



ETA-Danmark A/S
Göteborg Plads 1
DK-2150 Nordhavn
Tel. +45 72 24 59 00
Internet www.etadanmark.dk

Authorised and notified according
to Article 29 of the Regulation (EU)
No 305/2011 of the European
Parliament and of the Council of 9
March 2011

MEMBER OF EOTA



European Technical Assessment ETA-22/0805 of

I General Part

Technical Assessment Body issuing the ETA and designated according to Article 29 of the Regulation (EU) No 305/2011: ETA-Danmark A/S

Trade name of the
construction product:

Matacryl (one coat) bridge deck waterproofing system

Product family to which the
above construction product
belongs:

Liquid applied bridge deck waterproofing system

Manufacturer:

Alteco Technik GmbH
Raiffeisenstrasse 16
D-27239 Twistringen
Internet www.alteco-technik.de/

Manufacturing plant:

Alteco Technik GmbH
Raiffeisenstrasse
16 D 2739 Twistringen
Germany

This European Technical
Assessment contains:

8 pages including 1 annex which is an integral part of
the document

This European Technical
Assessment is issued in
accordance with Regulation
(EU) No 305/2011, on the
basis of:

European Assessment Document (EAD) No.
EAD 030675-00-0107: Liquid Applied Bridge Deck
Waterproofing Kits

This version replaces:

The ETA with the same number issued on 2023-03-01

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex(es) referred to above). However, partial reproduction may be made, with the written consent of the issuing Technical Assessment Body. Any partial reproduction has to be identified as such.

II SPECIFIC PART OF THE EUROPEAN TECHNICAL ASSESSMENT

1 Technical description of product

Matacryl (One Coat) Bridgedeck Waterproofing System is a medium viscosity, urethane-modified, pre-reacted 100 % solid membrane system based on acrylic monomers.

The Matacryl (One Coat) Bridgedeck Waterproofing System comprises:

- Matacryl Primer CM — a single-component reactive resin, based on methyl methacrylate
- Matacryl Waterproofing — a two-part urethane modified resin, based on methyl methacrylate, comprising Part A and B pigmented grey
- Matacryl STC Tack Coat — a single-component reactive resin pigmented grey, based on methyl methacrylate, for use with hot-rolled asphalt (HRA) surfacing
- Matacryl Tack Coat Number 1 – modified bonding bitumen for use to increase bond between substrate and asphalt (CBM) overlay
- Matacryl Catalyst — a 50% dibenzoyl peroxide with a solid plasticiser, for use in Matacryl Primer CM, Matacryl Waterproofing and Matacryl STC Tack Coat
- Natural quartz (0.3 to 0.7 mm) — fire-dried natural quartz sand, for broadcast into the applied Matacryl Primer CM or Matacryl STC Tack Coat (<100mm surfacing) when still wet
- Natural quartz (2.0 to 3.5 mm) — fire-dried natural quartz sand, for broadcast into the applied Matacryl STC Tack Coat when still wet (for surfacing >100mm)
- Matacryl Accelerator — a single-component, yellow-coloured resin solution, for use in Matacryl STC Tack Coat (where applicable), Matacryl Primer CM and Matacryl Waterproofing to accelerate curing at temperatures below 0°C
- Matacryl Adcol Thinner — a single-component colourless liquid, based on methyl methacrylate, for use in Matacryl Waterproofing to improve workability and flow. Also, used as a cleaner before overlapping with the system.

See annex A for consumption and thickness of the components.

This liquid applied bridge deck waterproofing kit is not intended to receive direct vehicular traffic in service and in this case will always be used beneath overlays of asphalt (mastic asphalt, asphalt concrete or concrete) which may have a protective character and/or additional waterproofing function. The kit (One Coat) Bridgedeck Waterproofing System is designed and installed in accordance with the manufacturer, design and installation instructions.

2 Specification of the intended use(s) in accordance with the applicable European Assessment Document (hereinafter EAD)

The intended use of Liquid Applied Bridge Deck Waterproofing Kits is the waterproofing of the concrete deck of the bridge preventing or controlling the passage of water to the support.

This kit is made of non-load bearing construction elements. It does not contribute directly to the stability of the bridge on which is installed, but it can contribute its durability by providing enhanced protection from the effect of weathering.

This applied kit fulfils the Basic works requirements n° 1 (Mechanical resistance and stability), n° 3 (Hygiene, health and the environment) and n° 4 (Safety in use) of the European Regulation 305/11.

The kit is suitable for the following use categories according: (A) with overlay and intended to receive vehicular traffic:

- A.1 Overlay asphalt concrete applied at $(160 \pm 10) ^\circ\text{C}$ (CBM).
- A.2 Overlay of mastic asphalt applied at $220 ^\circ\text{C}$ (MA).

In the manufacturer's technical dossier (MTD) to this ETA the manufacturer gives specific information concerning the application of the product.

Kits used beneath ballast are not covered under the scope of this ETA

Concerning product packaging, transport, storage, maintenance, replacement and repair it is the responsibility of the manufacturer to undertake the appropriate measures and to advise their clients on the transport, storage, maintenance, replacement and repair of the product, as the manufacturer considers necessary.

It is assumed that the product will be installed according to the manufacturer's instructions "Matacryl Installation Guide vAug23".

The provisions made in this European Technical Assessment are based on an assumed working life of the Matacryl (One Coat) Bridgedeck Waterproofing System of at least 25 years.

The indications given on the working life cannot be interpreted as a guarantee given by the manufacturer or the Assessment Body but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

3 Performance of the product and references to the methods used for its assessment.

Basic requirement for construction works 1; Mechanical resistance and stability					
Essential characteristic		Relevant clause in EAD		Condition test	Values
Bond strength (kit to support)		2.2.1		P1, S0, T5	3.04 MPa
Capacity to bridge cracks (-20 °C)	Asphalt concrete 160 °C (CBM)	2.2.2		P1, S1.2+S2, T2	Watertight
	P1, S1.1+S2, T2			Watertight	
Resistance to chloride ion penetration		2.2.3			Pass
Resistance to dynamic actions	Resistance to perforation	2.2.4	2.2.4.1	P1, S0, T5	Pass (I ₄)
	Resistance to compaction of asphalt concrete		2.2.4.2	P1, S1.2, T5	Resistant and watertight
Resistance to heat impact (indirect method) (150 °C)	Bond strength (kit to support)	2.2.5		P1, S1.1, T5	3.16 MPa
	Tensile stress (initial- ageing) 10 mm/min 23 °C / 1 mm/m -10 °C			P1, S1.1, T5 P1, S1.2, T5	-0,4% 9,7%
	Elongation (initial- ageing) εt 10 mm/min 23 °C / 1 mm/m -10 °C			P1, S1.1, T5 P1, S1.2, T5	-1,6% 6,3%
	Capacity to bridge cracks			P1, S1.1, T2	Watertight
Resistance to shear between the substrate and overlay	Mastic Asphalt 220 °C (MA)	2.2.6		P1, S1.1., T5	1,02 MPa*
	Mastic Asphalt 220 °C (MA)			P1, S1.1/S3, T5	1,91 MPa*
	Asphalt Concrete 160 °C (CBM)			P1, S1.2, T5	0.92 MPa*
Water-tightness (23 °C)		2.2.7		P1, S0, T5	Watertight
Resistance to high and low service temperatures	Low temperature	2.2.8	2.2.2	P1, S1.1+S2, T2	Watertight
	Bond strength to the support at +40 °C, -10 °C or -20 °C		2.2.1	P1, S3, T6 P1, S3, T3 P1, S0, T2	2.53 MPa 4.83 MPa
	Resistance to shear to support (2.2.6) at +40 °C and/or –10 °C		2.2.6	P1, S1.1/S3, T3	1.91 MPa
Capacity to penetrate pores in the support		2.2.9		P1, S0, T5 P2, S0, T5 T5	3.04 MPa 3.24 MPa 100-130 mPa-s (25°C)
		Viscosity			No performance assessed
		Viscosity		T1 – T4	
Resistance to flow (associated with the application to non- horizontal surfaces)		2.2.10		P1, S0, T5	0 %
Dry film thickness		2.2.11		P1, S0, T5	≥2.0 mm
Resistance to the effects of climatic conditions on application	Bond strength to the support 5 °C	2.2.12	2.2.1	P2, S1.1, T5	1.64 MPa
	Bond strength to the support 40 °C			P2, S1.1/S3, T5	1.43 MPa
Resistance to the effects of quality of the support (SC)	Moisture Content (MC)	2.2.13		P3, S0, T5	3.20 MPa
	Day Joints (OA) (24h/ 48h)			P4, S0, T5	3,70MPa A/B
	Section Joints (up to six months) (OA) (7d)			P4, S0, T5	3,53MPa A/B
Resistance to contact with water (Wa)	Variation in mass (edges not sealed)	2.2.14		P1, S5.1. T5	2,11 %
	Micro hardness Initial/ageing (variation)				97° / 92° (1,4 %)

Resistance to alkali solution contact (Al)	Variation in mass	2.2.15		P1, S5.2, T5	0.48 %
	Micro hardness Initial/ageing (variation)			P1, S5.2, T5	1.2 %
Resistance to oil, petrol or, diesel contact	Variation in mass	2.2.16		Hydraulic oil Diesel	0.16 % -4.78 %
	Micro hardness Initial/ageing (variation)			Hydraulic oil Diesel	-1.1 % 8.0 %
Resistance to bitumen contact (Bi)	Micro hardness Initial/ageing	2.2.17		P1, S5.3, T5	2,8 %
Resistance to heat ageing (HA)	Capacity to bridge cracks	2.2.18	2.2.2	P1, S0+S2, T2	Watertight
	Tensile stress (initial- ageing) 10 mm/min 23 °C / 1 mm/m -10 °C		2.2.18	P1, S0, T5 P1, S2, T5	8,8 MPa 10,0 MPa
	Elongation (initial- ageing) ϵ_t 10 mm/min 23 °C / 1 mm/m -10 °C		2.2.18		269 % 260 %
	Bond strength to the support		2.2.1	P1, S2, T5	4.21 MPa

*In the cases of the National regulations demand a specific minimum values of the resistance to shear between the kit and the overlay, this test shall be performed for the specific overlay used in each work.

Basic requirement for construction works 3: Hygiene, health, and the environment

Essential characteristic	Relevant clause in EAD	Performance
Content, emission and/or release of dangerous substances	2.2.20	No Performance assessed

Basic requirement for construction works 4: Safety and accessibility in use

Essential characteristic		Relevant clause in EAD	Condition test	Performance
Bond strength (kit to overlay)	Mastic Asphalt (220 °C):	2.2.21		1.27 MPa
	Asphalt concrete (160 °C):			1.23 MPa
Slipperiness		2.2.22		No performance assessed
Resistance to Abrasion / Wear		2.2.23		No performance assessed

Durability due to climatic Resistance to freeze/thaw (FT)

Essential characteristic	Relevant clause in EAD		Condition test	Performance
Bond strength to support	2.2.24	2.2.1	P1, S3, T5	1.78 MPa
Resistance to shear to support / overlay MA		2.2.6	P1, S3., T5	1.91 MPa

See additional information in section 3.5-3.6.

3.5 Methods of verification

The assessment of the performance of Matacrl (One Coat) Bridgedeck Waterproofing System in relation to the applicable BWR's has been made in accordance with the European Assessment Document (EAD) No. EAD 030675-00-0107: Liquid Applied Bridge Deck Waterproofing Kits.

3.6 General aspects related to the fitness for use of the product.

The European Technical Assessment is issued for the product based on agreed data/information, deposited with ETA-Danmark, which identifies the product that has been assessed and judged. Changes to the product or production process, which could result in this deposited data/information being incorrect, should be notified to ETA-Danmark before the changes are introduced. ETA-Danmark will decide if such changes affect the ETA and consequently the validity of the CE marking based on the ETA and if so whether further assessment or alterations to the ETA, shall be necessary.

The construction product is manufactured in accordance with the provisions of this European Technical Assessment using the manufacturing processes as identified in the inspection of the plant by the notified inspection body and laid down in the technical documentation.

Installation. The kit is installed on site. It is the responsibility of the manufacturer to guarantee that the information about design and installation of these kits is effectively communicated to the concerned people. This information can be given using reproductions of the respective parts of this European Technical Assessment. Besides, all the data concerning the execution shall be clearly indicated on the packaging and/or the enclosed instruction sheets using one or several illustrations.

Design. In the MTD the manufacture gives information on the quantities consumed and the processing, which shall lead to a thickness of the deck waterproofing ≥ 2.3 mm.

Usage range of temperatures. The range of operational temperatures of the waterproofing layer is -40 °C to $+60$ °C. EN 1991-1-5 provides a correlation between the shade air temperature and bridge temperature component.

Condition of support. The support on which the waterproofing is applied shall have a surface texture of 0.3 mm to 1.5 mm. EN 1766, clause 7.2 or EN 13036-1 describe suitable methods for measuring surface texture.

The age of the concrete support is normally assumed to be in excess of three weeks and unless specific

assessments have been made the cohesive strength of the concrete surface shall be greater than 1.5 MPa.

Weather conditions. The waterproofing system cannot be put in place during rain, hail or snow. The support temperature shall be greater than 5 °C and at least 3 °C above the dew point, unless specific assessments have been made.

Execution. Particularly, it is recommended to consider:

- The kit installation has to be carried out by qualified installers,
- it can only be used the components of the kit indicated in this ETA,
- the supervision of the amount of material used (kg/m^2) and the control visual to check that each coat cover totally the one below, can ensure the minimum thickness of the kits,
- inspection of deck surface (cleanliness and correct preparation) before applying the deck waterproofing,

4 Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base.

4.1 AVCP system

According to the decision 2003/722/EC as amended by 2001/596/EC, the system(s) of assessment and verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) is 2+.

5 Technical details necessary for the implementation of the AVCP system, as foreseen in the applicable EAD.

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at ETA-Danmark prior to CE-marking.

Issued in Copenhagen on by

Thomas Bruun
Managing Director, ETA-Danmark

Annex A

Consumption and thickness of the components

Component	Name	Consumption	Thickness
Primer	Matacril Primer CM	0,3 – 0,5 kg/m ²	0.4 mm (Average)
Waterproofing membrane	Matacril Waterproofing	≥ 2,8 kg/m ²	≥ 2.0 mm
Binding layer	Matacril STC Top Coat	0,5 – 0,6 kg/m ²	0.5 mm (Average)
Binding layer	Matacril Tack Coat Number 1	1 – 1,25 kg/ m ²	1mm (Average)
Catalyst	Matacril Catalyst	1 – 6 %, by weight	N/A
Low temperature accelerator	Matacril Accelerator	0.5 – 2 %, by weight	N/A
Thinning/cleaning agent	Matacril Adcol Thinner	≤ 5 %, by weight	N/A

