



# Peran RC

# **Product sheet**

## **Product description**

Peran RC is a 2-component, epoxy-based transparent binder with good resistance to light and resistant to early contact with water (24 hrs @ 20°C).

#### Uses

Peran RC is used as a binder for the Peran Rustik range.

### **Environment & Health**

Peran RC is a solvent and nonylphenol free product, and practically odourless during application. Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken.

For more information, please refer to the safety datasheets for the individual components.

## Ratio of components

2 parts of component A are mixed with 1 part of component B, by weight.

1.7 parts of component A are mixed with 1 part of component B, by volume.

Add all of Hardener B to Base A. Mix with slow speed drill and helical spinner, taking care not to entrain air. Add mixture to aggregate as prescribed in Application Instructions.

#### **Application temperature**

The recommended substrate temperature is 15-25°C, but no less than 10°C.

The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening. Temperatures should not fall below 5°C in the 24 hrs after application.

#### Application time/pot life

Ready-mixed product should be used within 30 minutes at a temperature of 18°C. At higher temperatures the application time is shorter.

## Curing time (20°C)

Can be overcoated after 15 hours.

Can be walked on after 15 hours.

The product is fully hardened after 5-7 days.

High humidity in the early stages of cure can result in white, matt surfaces (blooming).

Do not cover or wash within the first 16 hours of curing.

#### **Colours**

Transparent

## **Solids content**

Approx. 100 %

#### **Finish**

Gloss

# **Density**

Component A approx. 1.15 kg/l. Component B approx. 1.01 kg/l. A+B approx. 1.10 kg/l.

## **Storage**

12 months in unopened pack at a temperature of 5-40°C.

Protect from weather and moisture/contaminant ingress.

# **Packaging**

The product is delivered A+B in the following packs.

Unit Base A Hardener B

6.9 kg (6.3 litres) 4.6 kg 2.3 kg

This pack is mixed with 100kg of Natural Stone or 125kg of Glamour Stone.

CE Mark - see the Declaration of Performance for details.

Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

Flowcrete UK Ltd is an RPM company