

RW371

TREMPLY SEALANT

KEY BENEFITS SUMMARY

- Joint sealing properties
- Flexible
- Fire rated

PRODUCT INFORMATION

Description

RW371 is a halogen free, polymer emulsion-based fire rated sealant.

Usage / Purpose

RW371 is designed for use as a fire retarding sealant between joints of RW370 TremPly Protection Board.

Packaging

310ml cartridges

Availability

Direct from Tremco CPG UK Limited (see bottom of leaflet for address and telephone details).

Application

- Apply RW371 to the joints of the RW370 boards and allow to cure prior. Ensure boards are clean and free from dust, dirt and other contamination prior to application

Please Note

- Application temperature shall be above 5°C.
- Do not apply when rain is imminent.

Health & Safety Precautions

Safety data sheet must be read and understood before use.

Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge.

Tremco CPG UK Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

RW371

TREMPY SEALANT



TECHNICAL DATA

PROPERTY	RESULT
Composition	Polymer emulsion-based sealant
Skinning time	15 minutes to 1 hour depending on conditions
Cure time	5 - 15 days for 15mm x 20mm bead
Hardness Shore A	20 - 25
Temperature resistance	-20°C to +60°C
Application temperature	+5°C to 40°C
Movement accommodation	+7.5% Conforms to ISO 11600 7.5P
Coverage	One tube is sufficient to produce approx 1m using a 20mm x 15mm bead
Storage	Store in cool, dry conditions
Shelf Life	18 months when store in unopened containers