

RW536

ALPHAGUARD PUMA GP THIX



KEY BENEFITS SUMMARY

- Ideal for minor defects, bolt heads, cracks and complex detailing
- Easy to apply
- 100% waterproof
- Very fast curing; 60 minutes at +20°C
- Possibility to apply at very low temperatures (0°C)

PRODUCT INFORMATION

Description

RW536 is a two part thixotropic paste based on polyurethane modified methyl methacrylate.

Usage / Purpose

RW536 is a filler paste designed for dressing around sharp or uneven substrates.

NOTE: The pot life after mixing the RW536 with Catalyst is 10-15 minutes depending on the ambient temperature and the amount of Catalyst used.

Packaging

RW536 GP Thix: 25kg Drum

Availability

Direct from Tremco CPG UK Limited (see bottom of leaflet for address and telephone details).

Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

Surface Preparation

- The area to be waterproofed must be dry, clean, free from contamination and free of dirt, grease, oil and other elements which could prevent good adhesion to the substrate.
- Metal parts should be rust free and thoroughly prepared.
- Bubbles and imperfections should be repaired according to good roof practice.

Priming

- Typically no primer needed on asphalt, PVC, most bitumen felt, and glass. If in doubt, please contact Tremco CPG UK Limited's technical services on 01942 251 400
- For concrete, metal and ceramic substrates use RW512 Concrete Primer before application of RW536.

Mixing

- Prior to use, RW536 must be carefully stirred to achieve a uniform distribution of the paraffin contained in the product.
- Ensure the product is mixed using a suitable non-sparking/ATEX mixer.
- RW536 is then thoroughly mixed together with the Catalyst (50% dibenzoyl peroxide).
- The amount of catalyst powder to be added depends upon the temperature.

Dosage Chart

It should be noted that the amount of catalyst powder to be added depends upon the temperature.

Temperature	Weight % (Grams per 25kg)
30°C	1% (250g)
20°C	1.4% (350g)
10°C	2.8% (700g)
0°C	4% (1000g)

Application Instructions

- Apply by brush to be required area prior to carry out the main waterproofing works.
- Allow to cure, once fully cured the AlphaGuard PUMA system can be applied.

Cleaning

Clean tools immediately after use with RW593 Cleaner.

Health & Safety Precautions

Safety data sheet must be read and understood before use. Highly flammable - keep away from open flames and other ignition sources. Empty containers that have fully cured product residues can be considered as non-hazardous waste. Uncured product must be disposed of responsibly in accordance with local or national health and safety regulations. Please refer to the specific Tremco safety data sheet for further guidance.

Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge.

Tremco CPG UK Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

TECHNICAL DATA

PROPERTY	RESULT (Liquid State)
Composition	Based on polyurethane modified methacrylates
Tensile Strength	6.7 MPa
Elongation	282%
E-Modulus ISO 527	65 MPa
Density	1.36 g/ml
Viscosity (+ 25°C)	4000 mPa:s
Consumption	As required
Pot Life (20°C to 20°C)	± 15 minutes
Cure Time (20°C, 50% RH)	± 60 minutes
Rain Resistant	± 20 minutes
Application Temperature	from 0°C to +30°C
Storage	Store between +15°C and +25°C
Shelf Life	12 months when stored as recommended in original unopened containers