

RW623

ALUMANATION 301 SEAM SEALER



KEY BENEFITS SUMMARY

- Quick and durable joint sealing properties
- Easy to apply
- Versatile application

PRODUCT INFORMATION

Description

RW623 is a single component, high solids, moisture curing, polyurethane sealer.

Usage / Purpose

RW623 provides a flexible sealer for metal roof seams and fasteners penetrations.

Packaging

15kg drum

Colour

Black

Availability

Direct from Tremco CPG UK Limited (see back of leaflet for address and telephone details).

Protective Equipment

Ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

Surface Preparation

- The surface must be clean, dry, in sound condition, and free of loose coatings, dust, dirt, debris, and any other contaminants liable to prevent adhesion to the substrate.
- Rust must be abraded until it no longer exhibits flaking or chalking.

Application Instructions

- Apply Alumanation 301 Seam Sealer by brush working material into overlaps and around fasteners to completely encapsulate.
- Allow to completely dry before apply RW621.
- For application details refer to Tremco CPG UK Limited Technical Services.

Health & Safety Precautions

Safety data sheet must be read and understood before use.

Highly flammable - keep away from open flames and other ignition sources.

Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and and deemed accurate at the time of issue.

Tremco CPG UK Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

TECHNICAL DATA

PROPERTY	RESULT
Composition	Polyurethane sealer
Elongation	220%
Solids by volume	80%
Emittance	Initial - 0.39 / 3 Year Aged - 0.52
Curing Time	24 hours to tack free
Flash Point (ISO 1516)	48°C
Tensile Strength	270 psi
Application Temperature	5°C and rising
Coverage	As required
Storage	Store in dry, shaded conditions between +15°C and +20°C
Shelf Life	6 months when stored as recommended in original unopened containers