


Flowchem VE SL (3 mm)

A horizontal, self smoothing, shrinkage compensated, vinyl ester resin based floor screed system with excellent chemical and mechanical resistance.



- 1 Prepared Substrate
- 2 Flowchem VE Primer
- 3 Flowchem VE SL



UV Resistant:

Excellent resistance to deterioration from UV exposure over time.



Temperature Resistant:

High thermal resistance, up to 140°C.



Chemical Resistant:

Impressive resistance to aggressive chemicals and solvents.



Fast Cure:

Walk on 2 hours after curing at 20°C, reducing downtime.

TEMPERATURE RESISTANCE	
EN ISO 75	140°C
BARCOL HARDNESS	
EN ISO 59	>40
VOLUME SHRINKAGE	
Rili 4 2.5.3.2.1	<0.0003 %
COMPRESSIVE STRENGTH	
EN ISO 604	> 45 MPa
IMPACT RESISTANCE	
EN ISO 6272-1	≥ 20 Nm
BOND STRENGTH	
EN 1542	> 4 N/mm ² (substrate failure)
SLIP RESISTANCE*	
EN 13036-4 (typical values for 4-S rubber slider)	Dry >40 low slip potential

SPEED OF CURE**	20°C
Light Traffic	2 hrs
Full Traffic	24 hrs
Full Chemical Cure	24 hrs

The figures that follow are typical properties achieved in laboratory tests at 20°C and at 50% Relative Humidity.

*The slipperiness of flooring materials can change significantly, due to the installation process, after short periods of use, due to inappropriate maintenance, longer-term wear and/or surface contaminants (wet or dry). Textured systems are recommended to meet slip resistance value requirements for wet conditions and/or surface contaminants (wet or dry). Please contact our Technical Department for further details and specifications.

** The speed of cure can be controlled by varying the accelerator dosage level. The above times are based on the standard dosage level.



Dark Grey Close to RAL 7046 Light Grey Close to RAL 7035 Green Close to RAL 6002 Red Close to RAL 3009

The applied colours may differ from the examples shown. For a full colour chart and samples, contact your local CPG office.

Model Specification

System	Flowchem VE SL
Finish	Satin / Matt
Thickness	3 mm

Preparatory work and application in accordance with manufacturer's instructions.

Products Included In This System

Primer	Flowchem VE Primer @ 0.35 kg/m ²
Topping	Flowchem VE SL @ 5.4 kg/m ² for 3mm

NB: Specifications are written for each installation to meet the clients particular requirements.

Note: Flowchem VE SL resin already contains Flowchem VE Topcoat Additive, so the additive should not be used in the Flowchem VE SL system.

Substrate Requirements

Reinforced concrete substrates should be capable of producing 1.5 N/mm² "pull-off" values and, following preparation, be free from laitance, dust and other contamination. The substrate should be visibly dry with a moisture content not exceeding 75% RH as per BS8203 (4.5% on Tramex scale), and free from rising damp and ground water pressure.

Installation Service

The installation should be carried out by a Tremco CPG approved contractor with a documented quality assurance scheme. Obtain details of our approved contractors by contacting our customer service team or enquiring via our website www.flowcrete.eu.

Aftercare, Cleaning & Maintenance

Clean floors regularly using a single or double headed rotary scrubber drier in conjunction with a mildly alkaline detergent.

Environmental Considerations

The finished system is assessed as nonhazardous to health and the environment. The long service life and seamless surface reduce the need for repairs, maintenance and cleaning.

Environmental and health considerations are controlled during manufacture and application of the products by Tremco CPG staff and fully trained and experienced contractors.

Important Notes

Tremco CPG products are guaranteed against defective materials and manufacture and are sold subject to our standard 'Warranty, Terms and Conditions of Sale', copies of which can be obtained on request. Warranty does not cover suitability, fit for purpose or any consequential or related damages. Please review warranty in detail before installing the products.

CPG's products are guaranteed against defective materials and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies of which can be obtained on request. Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Tremco CPG constitute potential options only and do not constitute nor replace professional advice in such regard. Tremco CPG recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.

System Datasheet written for Tremco CPG. Please consult Technical Team in your own country region for specific details. [13/12/23, 01 UK]