

CP720 AlphaGuard® BIO Base Coat

BIO-BASED POLYURETHANE BASE COAT



KEY BENEFITS SUMMARY

- **Bio Content**
 - High bio content makes product sustainable and environmentally friendly
- **Catalysed Cure**
 - Results in faster cure times than similar one-component products
- **Versatile**
 - Suitable for use over many substrates/ roof types
- **High Solids**
 - 100% solids
- **Low VOC**
 - Low odour
 - Meets California VOC limits
- **Chemical Resistant**
 - Resistant to a wide variety of harmful chemicals

PRODUCT INFORMATION

Description

CP720 is a two-part, bio-based, polyurethane roof coating. CP720 is used with fibreglass mat or polyester reinforcement.

Usage / Purpose

The AlphaGuard BIO System can be used in a variety of refurbishment and new construction projects, including: warm roof, inverted roof and vegetative roof systems.

Packaging

Part A - 20 litre pail containing 12.9 litres
Part B - 3.78 litre pail containing 2.15 litres
Each Part A & Part B kit yields 15 litres

Colour

Grey

Availability

Direct from Tremco CPG UK Limited (see bottom of leaflet for address and telephone details).

Protective Equipment

USE IN WELL VENTILATED CONDITIONS and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.

Preparation

- Clean the substrate with a high pressure power wash of at least 13.5 MPa.
- Prior to application the surface must be clean, dry, solid, and free of dirt, grease, oil, algae and any other contaminants that would be detrimental to an acceptable bond being achieved.

Mixing

- Use a heavy duty power drill with Jiffy Mixer attachment. Cordless drills are not recommended and may not properly mix the materials.
- Mix Part A for 1 minute before adding Part B.
- After adding Part B mix the combined materials for a minimum of 2 minutes moving the mixing blade from top to bottom.

- Make sure to mix areas around side walls and bottom of pail. Improper mixing will result in non-curing material. Never fully invert empty pails in attempt to drain material - will result in non-curing material.
- Do not break down kits into smaller quantities - MIX ENTIRE KIT.

Application Method

- Brush/roller/squeegee

Application Instructions

Repairs

- If CP720 is being used over an existing roof system, all appropriate repairs should be made before applying the AlphaGuard BIO system.
- Allow suggested cure time of repairs before applying CP720 to the roof surface.

Reinforcement

- Reinforcement: CP720 requires full reinforcement with CP585 AlphaGuard Glass Mat or CP582 Polyester Fabric.
- Fully embed reinforcement into wet coating using a brush or roller until free of voids, wrinkles, air pockets, standing fibres, etc.

Acceptable Roof Surfaces

Bituminous Roof Systems

- CP720 can be used over aged asphalt based roof products. When using over felt roof systems, repair any blisters and degraded felts.

Concrete

- CP720 can be used directly over concrete with the appropriate primer. Any cracks should be repaired before coating is applied. Allow new concrete to fully cure for a minimum of 28 days (a concrete dryness test should be performed before application).

Single Ply Systems

- CP720 can be used over select single ply systems, when used with the appropriate primer.

Modified Bitumen Systems

- CP720 can be used over MB roof systems when used with the appropriate primer.

CP720 AlphaGuard® BIO Base Coat

BIO-BASED POLYURETHANE BASE COAT

TREMCO

Cleaning

Before the product cures, clean surfaces and equipment with isopropyl alcohol.

Please Note

- Do not apply when ambient temperatures are below 7°C
- Do not apply when overnight temperature drops below 4°C
- Do not adhere to expanded polystyrene or extruded polystyrene.
- Do not apply directly to plywood, tongue and groove decks, wood decks, poured in place gypsum, lightweight insulating concrete decks, structural lightweight concrete and cementitious wood fibre decks.
- Not for use over coal tar pitch, gravel BUR, corrugated metal roof systems, and silicone-based coatings and sealants.

Health & Safety Precautions

Safety data sheet must be read and understood before use.

Technical Service

Tremco CPG UK Limited has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

Tremco CPG UK Limited products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG UK Limited written instructions and (b) in any application recommended by Tremco CPG UK Limited, but which is proved to be defective, will be replaced free of charge. No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. Tremco CPG UK Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

TECHNICAL DATA

PROPERTY	RESULT
Composition	Two-part, bio-based, polyurethane
External Fire Performance (CEN/TS 16459:2013)	Within the Broof (T4) classification CP720 AlphaGuard BIO Base Coat & CP820 AlphaGuard BIO Top Coat tested together as a system
Tensile Strength (ASTM D412)	9.7 MPa
Water Vapor Transmission (ASTM E96)	0.13 metric perms
Low Temperature Flexibility (ASTM D522)	Pass at -31.7°C (12.7 mm mandrel bend)
Tear Strength (ASTM D5147)	140 kg
Water Absorption (ASTM D471)	0.008
Indentation Hardness (ASTM D2240)	72 Shore A
Dimensional Stability (ASTM D5147)	< 0.1%
Volume Solids (ASTM D 2697)	100%
Weight Solids (ASTM D 1644)	100%
Viscosity (ASTM D 2196)	2,500 - 5,500 cp (mPas)
Pot Life (25°C/50% RH)	20 - 25 minutes Temperature dependent - Increasing temperature reduces expected pot-life
Skin Time (25°C/50% RH)	3 - 4 hours
Over-Coat Time (25°C/50% RH)	6 - 7 hours
Coverage	Smooth BUR/MB, Concrete, Single-Ply surfaces: Minimum 1.2 l/m ² Granule surfaced MB: Minimum 1.6 l/m ²
Storage	Store in dry shaded conditions between +15°C and +26°C and low humidity. Storage temperatures must not exceed 43°C. Do not store in direct sunlight.
Shelf Life	12 months when stored as recommended in original unopened packaging