

| | | | |
|---------------|--|-----|--|
| Cl/SfB | | Yt3 | |
| CAW Z20 | | | |
| Uniclass L673 | | | |

Description

SP050 is a multi-purpose sealant and adhesive based on tremco illbruck's advanced SP polymer formulation.

Colour

White, grey and black. Other colours available subject to minimum order quantity.

Crystal clear version available, refer to SP030.

Packaging

310 ml cartridges (12 per carton)

Technical Information

| Property | Test Method | Results |
|----------------------------|---|---------------------------------|
| Composition | | Advanced SP polymer formulation |
| Specific Gravity | DIN 52451-A | 1.6 |
| Consistency | EN 27390 20 mm profile | 0 mm , non-sagging |
| Shore A Hardness | | 50 |
| Shrinkage | DIN 52 451 | 3% |
| Modulus at 100% Elongation | EN 28 340 | 1.7 N/mm ² |
| Tensile Strength | DIN 53 504 S2 | 2.1 N/mm ² |
| Elastic Recovery | EN 27 389-B | > 50% |
| CureTime (at 20°C) | | ~ 2.5 mm/1st day |
| SkinningTime | @23°C and 50% RH | ~ 17 minutes |
| Application Temperature | | +5°C up to +40°C |
| Service Temperature | | -40°C up to + 90°C |
| Storage | Store in shaded dry conditions between +5°C and +25°C. | |
| Shelf Life | 18 months when stored as recommended in original unopened containers. | |

Necessary Tools

- Standard cartridge skeleton gun and a sharp knife to cut nozzle.

Protective Equipment

Use in well ventilated conditions and ensure all recommended protective equipment is worn during handling & use of this product. For full recommendation, refer to safety data sheet.


Preparation

- May be applied to damp substrates.
- For optimum adhesion, surfaces should be clean, dry, sound and free of contamination.
- Always carry out a test to confirm compatibility prior to use.
- Roughen non-porous surfaces.
- On materials such as glass, aluminium, ceramics, lacquered wood, epoxy and polyester no primer is required. For other materials, please contact tremco illbruck Technical Services.



SP050

Fix & Seal Universal



Usage / Purpose

SP050 provides a high strength flexible bond in a wide variety of construction and industrial applications. Typical uses include the bonding of skirting boards, battens, slats, door thresholds, acoustic panels (and similar sheet materials), etc.

Key Benefits

- A green alternative to traditional polyurethane adhesives- does not contain solvents or isocyanates and is very low odour
- Excellent adhesion to a wide range of materials including metals, glass, PVC and concrete
- Tack free in less than 30 minutes
- Excellent weather resistance- suitable for internal and external applications
- Can be overpainted once cured

Application

- Cut off end of thread with a sharp knife, avoiding damage to the thread. Trim the nozzle to the required diameter
- Ensure good contact between the joint surfaces before applying adhesive. Apply a bead of adhesive to one or both surfaces. For larger bond areas, spread the adhesive immediately using a notched spreader
- Bring the two components together immediately and clamp securely together for at least 30 minutes until sufficient bond strength has developed. Sufficient working strength will normally develop after 30 minutes.

Coverage

| Width | Depth |
|---------|-------|
| 5 x 5 | 12.4 |
| 8 x 6 | 6.4 |
| 10 x 8 | 3.8 |
| 15 x 10 | 2.0 |
| 20 x 12 | 1.2 |
| 25 x 15 | 0.8 |
| 30 x 15 | 0.6 |

Cleaning

Remove excess adhesive immediately with AT200 High Strength Cleaner. Ensure surface is solvent resistant before cleaning. Cured adhesive can only be removed mechanically.

Please Note

Not suitable for bonding polyethylene, polypropylene, Teflon® or nylon. Not recommended for sheet laminate. Not recommended for use on synthetic materials sensitive to stress cracking. Not suitable for constantly submerged joints. Do not use as a structural glazing adhesive. When bonding to copper or brass, please consult tremco illbruck technical services for priming details.

Health & Safety Precautions

Safety data sheet must be read and understood before use.

Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco

illbruck written instructions and (b) in any application recommended by Tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct. tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.



tremco illbruck Limited
Coupland Road, Hindley Green
WN2 4HT Wigan
United Kingdom
T: +44 1942 251400
F: +44 1942 251410

info.uk@tremco-illbruck.com
www.tremco-illbruck.co.uk